

Product Specifications

Dreamscape Bling/Prisma

PHYSICAL PROPERTIES

Product Width:	54" wide
Product Weight:	20 oz. per lineal yd. (13oz. per sq. yd.)
Vinyl Weight:	17 oz. per lineal yd.
Fabric Weight:	3 oz. per lineal yd.
Thickness:	0.030 in.
Fabric:	Poly-Cotton Osnaburg

BREAKING STRENGTHS, LBS. FORCE

Machine Direction-warp:	*Exceeds Type II minimum of 50 lbs.
Cross Machine Direction-fill:	*Exceeds Type II minimum of 55 lbs.

TEARING STRENGTH, SCALE

Machine Direction-warp:	*Exceeds Type II minimum of 25lbs.
Cross Machine Direction-fill:	*Exceeds Type II minimum of 25 lbs.

COLD CRACK RESISTANCE @ 20°F

No change

HEAT AGING (7 DAYS @ 158°F)

*Does not become stiff, brittle, discolored, or show loss of grain

SPECIFICATIONS / TESTING / CERTIFICATION

Federal Specification:	CCC-408-D,C,B,A Type II
CFFA Specification:	CFFA-W-101-D Type II

FIRE TESTING

ASTM-E84 Tunnel Test:	Class A
NFPA286 Corner Burn Test:	Class A
NFPA265 Corner Burn Test:	Class A
BS476 Part 6&7	

*Meets or exceeds requirements for flame spread, smoke developments and flashover.

MOLD/MILDEW/BACTERIAL RESISTANCE

ASTM-G21 Specifications:	Passed all requirements of CCCW-408-D
--------------------------	---------------------------------------

ENVIRONMENT

NYC MEA: Register Cadmium and Lead Free Formulation