



INTERIOR SOLUTIONS

DOOR SKINS

Upgrade your flat panel interior doors by resurfacing with **MDC Door Skins** — an easy, cost-effective way to achieve a fresh, modern look. Skip the hassle and expense of replacing damaged or older doors entirely. This eco-friendly solution keeps your old doors out of the waste stream, making it a smart choice for your space and the planet.

MDC Door Skins are designed for easy installation. Over-sized skins are easily fabricated and cut and adhered onsite with budget-friendly, locally purchased 3M Fastbond 30-NF adhesive. MDC Door Skins can also be provided with an adhesive backing at additional cost. Offering exceptional durability, they deliver a refreshed appearance and long-lasting protection against wear and tear.

Available in a wide variety of wood grain finishes, MDC Door Skins are an ideal choice for both commercial and residential spaces. They create a warm, inviting entryway while saving time and money.



Why Choose MDC Door Skins?

- Large Stocked Selection
- Non-Stocked Options Available
- Impact/Scratch/Abrasion/Chemical Resistant
- Easy to Clean Surfaces
- Easy Installation
- Fire Rated (with Recommended Adhesive)
- Fits Most Door Sizes
- Custom Sizes Easily Provided



TECHNICAL SPECIFICATIONS

PROPERTY	TEST METHOD	TYPICAL VALUE
Light fastness	DIN EN ISO 4892-2, 2006-06 DIN EN ISO 105 B 02, 2002-07	> 6 (blue scale)
Chemical Resistance	DIN EN 12720, 1997-10 (test substances and exposure times acc. DIN 68861/1, 2001-04)	Class 1 B (*1)
Scratch Resistance	DIN 68861/4, 1981-12	Class 4 D (> 1,0-1,5 N)
Resistance to Dry Heat	DIN 68861/7, 2001-04	Class 7 C (100°C)
Abrasion Resistance	DIN 68861/2, 1981-12	Class 2 B (> 350-650 rpm)
Tensile Strength	DIN EN ISO 527-3/2/200, 2003-07	Longitudinal > 40 N/mm ² Transverse > 30 N/mm ² (depending on embossing)
Gloss Level Tolerances	DIN 67530, 60° measuring head, 1982-01	< 15 +/- 2 16 to 30 +/- 3 31 to 50 +/- 5 > 50 +/- 7

NEMA STAIN RESISTANCE RESULTS (LD-3.4 2000) - CLEANING STEPS

TEST MATERIAL	0	1	2	3	4	SCORE	STAIN
1. Distilled Water						0	
2. Ethyl Alcohol/Water = 50/50						0	
3. Acetone	1	1	1	1	1	5	Moderate
4. Household Ammonia						0	
5. Citric Acid 10%						0	
6. Vegetable Oil						0	
7. Coffee	1					1	
8. Tea						0	
9. Tomato Catsup						0	
10. Mustard						0	
11. 10% Povidone Iodine	1					1	
12. Black Permanent Market	1	1				2	
13. #2 Pencil	1	1				2	
14. Wax Crayon	1	1				2	
15. Black Shoe Polish	1	1	1			3	